TRANSPORTATION

Marshall Space Flight Center CDDF Success Story Number 1

Robust Low-Cost Aerospike Combustion Chamber

Next-generation, regeneratively cooled rocket engines will require materials that can withstand high temperatures while retaining high thermal conductivity. A Center Director's Discretionary Fund (CDDF) project was initiated to develop and demonstrate a robust low-cost Aerospike combustion liner, utilizing vacuum plasma spray (VPS) functional gradient coating techniques, developed in the MSFC Microgravity Program. The thermal barrier coatings combined with the high-temperature properties of Cu-8Cr-4Nb, developed at LeRC, will further enhance the operating life and performance of liquid rocket engines. Thermal analysis showed that a 0.0035-inch NiCrAlY coating applied to Cu-8Cr-4Nb will lower the operating temperature of the liner by 200 °F, increasing liner life and reducing maintenance costs. Parameters were developed, bulk Cu-8Cr-4Nb material was VPS deposited onto cylindrical mandrels, and properties specimens were machined from the VPS- formed shell. The heat treated VPS tensile specimens had a density 99.2 percent of theoretical.

Testing showed that the ultimate tensile strength (UTS) of VPS Cu–8Cr–4Nb at 1,000 °F was 197 mega Pascal (MPa) or 50 percent stronger at operating temperature than the X–33 and SSME baseline alloy, NARloy–Z. Yield strength was 179 MPa, an 84 percent improvement for the VPS Cu–8Cr–4Nb. This work demonstrated that VPS Cu–8Cr–4Nb offers significant properties improvement over the existing alloy material, NARloy–Z, and is very timely, taking the fact that it is questionable that NARloy-Z is strong enough to contain the thrust needed to lift RLV into lower Earth orbit. A Cu–8Cr–4Nb liner has been VPS sprayed with the NiCrAlY functional gradient coating, to demonstrate a 200 °F drop in liner temperature, giving longer combustion chamber operating life and reduced maintenance costs. The heat treated and machined VPS Cu–8Cr–4Nb liner will be HIP brazed in a Lewis Research Center spoolpiece support jacket and hot fire tested this summer.